

## Strength grading of timber in the UK and Ireland in 2021

Dan Ridley-Ellis, David Gil-Moreno & Annette M. Harte

To cite this article: Dan Ridley-Ellis, David Gil-Moreno & Annette M. Harte (2022): Strength grading of timber in the UK and Ireland in 2021, International Wood Products Journal, DOI: [10.1080/20426445.2022.2050549](https://doi.org/10.1080/20426445.2022.2050549)

To link to this article: <https://doi.org/10.1080/20426445.2022.2050549>



© 2022 The Author(s). Published by Informa UK Limited, trading as Taylor & Francis Group



Published online: 19 Mar 2022.



Submit your article to this journal [↗](#)



View related articles [↗](#)



View Crossmark data [↗](#)

## Strength grading of timber in the UK and Ireland in 2021

Dan Ridley-Ellis <sup>a†</sup>, David Gil-Moreno <sup>b‡</sup> and Annette M. Harte <sup>b</sup>

<sup>a</sup>Centre for Wood Science & Technology, Edinburgh Napier University, Edinburgh, UK; <sup>b</sup>School of Engineering & the Ryan Institute, National University of Ireland Galway, Galway, Ireland

### ABSTRACT

This paper summarises the state of the art for strength grading of construction timber grown in the United Kingdom and the Republic of Ireland. It includes the latest approvals based on recent research on spruce, larch and Douglas-fir. It lists the following information along with the primary references: visual grading grades and strength class assignments; grading machines with approved settings for machine control grading; the species, size ranges and strength class combinations covered; and grade determining properties of specific strength classes for the UK and Irish markets. This paper is useful for those grading timber, and those specifying UK and Irish grown timber.

### ARTICLE HISTORY

Received 7 September 2021  
Revised 29 November 2022  
Accepted 1 March 2022

### KEYWORDS

Grades; classes; machine strength grading; visual strength grading; structural timber; EN14081

## Introduction



In Europe, structural timber is graded under the system set out by the European standard EN14081-1 and its supporting standards (e.g. Lycken et al. 2020). It sorts rectangular cross-section timber into categories based on required characteristic values of grade determining properties. For normal construction timber those primary (grade determining) properties are usually bending strength, bending stiffness and density (at 12% reference moisture content).

Instead of bending, grading can also be based on tension strength and stiffness. Either way, characteristic values of strength and density are specified as fifth percentiles and stiffness by the mean. No tension grading has yet been established for UK and Irish grown timber (although some testing has been done: Ó Fátharta et al. 2020; Gil-Moreno et al. 2019a). In the case of grading established on the basis of bending testing, the tension strength is one of the secondary properties, calculated from equations in EN384. In the case of grading on the basis of tension testing, the bending strength is a secondary property. Grading based on tension testing is most commonly done for glulam production, since tension strength is more important for the design. Since little UK and Irish is currently used for glulam manufacture, there has been no priority for developing tension based grading for this resource.

The UK and Ireland have very similar climatic conditions and forest management, and a long-established

exchange timber market with logs crossing the border. This is one of the reasons that modern grading rules usually treat both countries as a single growth area, particularly for Sitka spruce but also more recently for Douglas-fir (Gil-Moreno et al. 2019b) and larch. Collaborative research between Edinburgh Napier University and the National University of Ireland Galway, in the 'Strategic Integrated Research in Timber' projects and the 'WoodProps for Ireland' programme have confirmed the timber to be suitably similar for the purposes of grading. The research has also shown that the resource is dissimilar to timber grown elsewhere in Europe, with grading tending to be limited by wood stiffness for spruce and larch, as opposed to strength in other places. This is due to differences in climate, forest management, species choice and seed selection. One major difference is higher wind exposure; its effects on wood properties and limits on rotation length.

This paper covers the position in the UK and Ireland as of December 2021 and is for guidance only. When grading, the primary references should be consulted, noting that new assignments and settings can be added, existing ones can be changed, and even the definition of EN338 strength classes may change. The machine grading reports listed are confidential, but the reference number helps to identify the relevant machine settings table. Contact the machine manufacturer or a Notified/Approved Body to obtain more information about specific settings.

**CONTACT** Dan Ridley-Ellis  d.ridleyellis@napier.ac.uk  Centre for Wood Science & Technology, Edinburgh Napier University, Edinburgh, UK

<sup>†</sup>Convenor of CEN/TC124/WG2/TG1 "task group for machine grading settings & visual grading assignments for EN1912".

<sup>‡</sup>Secretary of CEN/TC124/WG2/TG1 "task group for machine grading settings & visual grading assignments for EN1912".

© 2022 The Author(s). Published by Informa UK Limited, trading as Taylor & Francis Group

This is an Open Access article distributed under the terms of the Creative Commons Attribution-NonCommercial-NoDerivatives License (<http://creativecommons.org/licenses/by-nc-nd/4.0/>), which permits non-commercial re-use, distribution, and reproduction in any medium, provided the original work is properly cited, and is not altered, transformed, or built upon in any way.

## Current grading possibilities

There are two parallel systems for grading: visual and machine, both of which follow the same basis: timber is sorted into grades according to a non-destructive assessment that is predictive of the grade determining properties; and the collective characteristic properties of the timber sorted into those grades determines the strength class (see Ridley-Ellis et al. 2016a for a more detailed explanation). The timber design properties are therefore usually specified with reference to one of the strength classes listed in the European standard EN338, although there are other strength classes in use (see below). It is also possible to declare all properties directly, without reference to a strength class.

The so-called ‘user-defined’ strength classes are convenient when grading for particular uses, as part of a fabrication process, or for a specific customer, since it makes better use of the real properties of the graded timber and/or the performance requirements for the intended use (see Ridley-Ellis et al. 2016b for discussion of the potential for this, and illustration with UK grown timber). The definition of UK and Irish specific strength classes is given in Table 1. Also included is TR26, which has been in long standing common usage in the trussed rafter industry in the UK and Ireland, and has its origins in previous design codes. The other strength classes are more recent and were developed to maximise the potential of home-grown timber.

Species are commonly grouped for grading, in which case the individual species do not have to be differentiated during production. The species and species groupings in use for UK and Irish grown timber are listed in Table 2. These groups are based on

**Table 2.** Species codes and combinations in use with UK and Irish grown timber.

Group	Common name	Botanical name	Reference
British spruce WPCS	Sitka spruce PCST	<i>Picea sitchensis</i>	EN14081-1:2016 (SB2)
	Norway spruce PCAB	<i>Picea abies</i>	
British pine WPNN	Scots pine PNSY	<i>Pinus sylvestris</i>	EN14081-1:2016 (SB2)
	Corsican pine* PNNL	<i>Pinus nigra</i> subsp. <i>laricio</i>	
Larch WLAD	European larch LADC	<i>Larix decidua</i>	EN14081-1:2016 (SB2)
	Hybrid larch LAER	<i>Larix × marschinsii</i> (syn. <i>L. × eurolepsis</i> )	
	Japanese larch LAKM	<i>Larix kaempferi</i>	
Douglas-fir	Douglas-fir PSMN	<i>Pseudotsuga menziesii</i>	EN13556:2003 (Tab2)
Oak	European oak QCXE	<i>Quercus petraea</i>	EN13556:2003 (Tab1)
		<i>Quercus robur</i>	
Sweet chestnut	Sweet chestnut CTST	<i>Castanea sativa</i>	EN13556:2003 (Tab1)

\*The standards and machine settings tables use the more general specification *Pinus nigra*, but with the relatively large volume of Corsican pine planted in the UK, and the more specific designation in older versions of BS5268-2, it can be assumed to refer to this.

long standing practice and reflect the mixtures grown and harvested together, although single batches of timber may well be of only one species. Note that the name ‘British spruce’ suggests a certain geographical origin, but that is not part of the species combination definition and the mix of Sitka and Norway spruce is also used elsewhere. Research is currently

**Table 1.** Definition of UK and IE specific strength classes (reference moisture content is 12%). Year of approval in bold.

Class	Better than EN338	5th percentile strength (N/mm <sup>2</sup> )	Mean stiffness (kN/mm <sup>2</sup> )	5th percentile density (kg/m <sup>3</sup> )	Reference (first report to use)
		Bending			
TR26	>C24	28.3	11.0	370	See *
C16+	>C16	18.5	8.0	330	TG1/ <b>2014</b> 10/34rev
NapierSA	>C24	25.0	11.0	375	TG1/ <b>2017</b> 03/27rev (intended for use with spruce)
NapierSB	>C22	22.0	10.0	360	
NapierSC	>C16	16.0	8.0	320	
NapierSD	>C14	15.0	7.0	310	
NapierLA	>C30	30.0	13.0	480	TG1/ <b>2017</b> 03/26rev (intended for use with larch)
NapierLB	>C27	28.0	12.0	440	
NapierLC	>C18	21.0	9.0	400	
NapierLD	>C16	20.0	8.0	390	
NapierDA	>C35	35.0	13.0	460	TG1/ <b>2018</b> 04/25 (intended for use with Douglas-fir)
NapierDB	>C30	30.0	12.0	460	
NapierDC	>C16	16.0	10.0	400	
NapierDD	>C14	14.0	9.0	400	
batten14	>C14	14.0	7.5	330	TG1/ <b>2018</b> 10/16 (intended for small dimension spruce)
batten12	–	12.0	7.5	330	
batten10	–	10.0	7.0	330	

\*TR26 was introduced in 1996. Limit states characteristic values were later listed in EN14081-4. See also Trussed Rafter Association 2021.

under way to extend these species combinations for more flexible grading (Ridley-Ellis 2020).

Visual grading is carried out according to grading rules that are usually (but do not have to be) national standards. Assignment to a strength class is specific to a combination of grading standard and timber source. Assignments to EN338 strength classes that have been approved by CEN TC124/WG2/TG1 and its predecessors are listed in EN1912. The standard is currently being updated to include the most recent assignments. There are no new visual grading approvals for UK or Irish grown timber to be included. However, the revision of EN1912 is expected to include a change to reflect equivalence between these two countries, of the national softwood grading standards (BS4978 and IS127) and the timber. The current visual assignments for the timber grown in the two countries grown are listed in Tables 3 and 4. When intending to use a particular species, grown in the UK or Ireland, it is important to consider what visual strength classes are possible, and to design and specify accordingly.

Machine grading can be by machine control or output control. Output control requires the producer to periodically test batches of graded timber and, if necessary (by statistical procedures), adjust the

grading machine settings to ensure grading proceeds correctly and efficiently. This method is not common in Europe, but it allows the use of any grading machine that meets the general requirements of EN14081. The much more common method is machine control, where settings are determined by previous testing and the grading machines of a certain model are expected to have identical performance. These settings are examined and approved by European Committee for Standardization (CEN) committee TC124/WG2/TG1 ("TG1"), which consists of a panel of experts with sufficient experience to be able to identify potential problems separate from simple compliance with the standards. See <http://blogs.napier.ac.uk/cwst/tg1/> for the latest additional rules and guidelines from TG1.

Table 5 shows a summary of the grade determining properties (as means and coefficients of variation) for the species that can be machine graded in both countries. For spruce, Douglas-fir and larch these are based on datasets from recent grading settings work (by Edinburgh Napier University and the National University of Ireland Galway) using current standards. For Scots pine the dataset has not been used for grading settings work, but is considered representative of the resource (it is a combination of unpublished data from BRE, Forest Research, Edinburgh Napier University, and the National University of Ireland Galway, Moore et al. 2008 and Ó Fátharta et al. 2020). A range is quoted as a rough approximation of the typical production variation from batch to batch. For spruce, there is a more scientific exploration of that variation at forest level given in Moore et al. 2013. For Douglas-fir there is an exploration at grading level in Gil-Moreno et al. 2019b. Additional information on the wood properties and uses of Sitka spruce and Scots pine can be found on Moore (2011) and McLean (2019).

Machines currently approved for machine control grading are listed in Table 6. Currently available

**Table 3.** Visual grading assignments for timber grown in UK and Ireland when grading with BS4978 or IS127 to EN338.

Species	Source	Visual grade To IS127	Strength class	Reference
Norway spruce Sitka spruce	IE	GS	C14	EN1912:2012 (\$6)
Norway spruce Sitka spruce	IE	SS	C18	EN1912:2012 (\$6)
To BS4978				
British spruce (Sitka & Norway)	UK	GS	C14	EN1912:2012 (\$6)
		SS	C18	EN1912:2012 (\$6)
British pine	UK	GS	C14	EN1912:2012 (\$6)
		SS	C22	EN1912:2012 (\$6)
Larch	UK	GS	C16	EN1912:2012 (\$6)
		SS	C24	EN1912:2012 (\$6)
Douglas-fir	UK	GS	C14	EN1912:2012 (\$6)
		SS	C18	EN1912:2012 (\$6)
		SS*	C24	PD6693-1:2019 (\$7.2)

Note 1: Assignment via BSI Published Document PD6693-1, possible in combination with the UK National Annex to BSEN1995-1-1, is on the basis of long standing use without problems (assignment was in BS5268-2).

Note 2: It is expected the continuing revision of EN1912 will extend the assignments of BS4978 to apply to IS127 and to change the source of spruce for both standards to UK and IE.

\* cross-section area >20,000 mm<sup>2</sup>, width and thickness ≥ 100 mm.

**Table 4.** Visual grading assignments when grading with BS5756.

Species	Source	Visual grade	Strength class	Reference
Oak	UK	TH2	D24	PD6693-1:2019 (\$7.1)
		TH1	D30	PD6693-1:2019 (\$7.1)
		THB*	D30	PD6693-1:2019 (\$7.1)
		THA*	D40	PD6693-1:2019 (\$7.1)
Sweet chestnut	UK	TH1	D24	PD6693-1:2019 (\$7.1)

Note: Assignment via BSI Published Document PD6693-1, possible in combination with the UK National Annex to BSEN1995-1-1, is on the basis of long standing use without problems (assignment was in BS5268-2).

\*cross-section area >20,000 mm<sup>2</sup>, width and thickness ≥ 100 mm.

**Table 5.** Typical average properties of UK and IE grown softwoods before grading (Of a batch of timber at 12% moisture content, with the EN384  $k_h$  factor).

	Dataset size	Mean bending strength (N/mm <sup>2</sup> )	Mean bending stiffness (kN/mm <sup>2</sup> )	Mean density (kg/m <sup>3</sup> )
Sitka and Norway spruce	~2000	30–33 (CoV 30%)	7.5–8.5 (CoV 30%)	380–410 (CoV 10%)
Scots pine	~500	36–46 (CoV 30%)	8.5–10.0 (CoV 30%)	480–550 (CoV 10%)
European, Japanese and hybrid larch	~1000	37–44 (CoV 30%)	9.5–10 (CoV 25%)	480–530 (CoV 12%)
Douglas-fir	~700	28–50 (CoV 35%)	8.5–13 (CoV 25%)	450–550 (CoV 10%)

settings for British and Irish grown timber are listed in [Table 7](#) (spruce), [Table 8](#) (pine), [Table 9](#) (larch) and [Table 10](#) (Douglas-fir). The existence of grading settings for a species and strength class does not mean that the grades will be easily available on the market. Most producers currently aim for maximum yield on a single grade-reject setting that produces the grades commonly placed on the UK and Irish markets, most commonly C16.

Certain machines can work in different modes, and use the settings approved for a different machine, typically from the same manufacturer.

Machines from different manufacturers with proven performance equivalence, and agreement of the manufacturers, can also use the same settings. Note that machine grading is based on the assessment of the grade determining properties by methods summarised in [Table 6](#). This is a separate route from visual grading, and parameters like knot size and ring width are not inherent in the definition of the strength classes, which are concerned with the actual characteristic properties. This means that machine grading will pass some pieces that fail visual grading rules and reject some pieces that

**Table 6.** List of grading machines approved for machine control. In bold the machines with machine control settings available for UK and Ireland.

Manufacturer	Name	ID*	Description
Tecmach Ltd	<b>Cook Bolinders</b>	1	Mechanical bending
Measuring and Process Control Ltd	<b>Computermatic Micromatic</b>	2	Mechanical bending
VTT	<i>Raute Timbergrader</i>	3	Mechanical bending
Microtec s.r.l. – GmbH	<i>EuroGrecomat-702</i>	4	X-ray
	<b>Goldeneye 702/802</b>	5	X-ray
	<i>EuroGrecomat-704</i>	6	X-ray & mechanical bending
	<b>Viscan</b>	8	Longitudinal resonance
	<i>EuroGrecomat-706</i>	9	X-ray & longitudinal resonance
	<b>Goldeneye 706/806</b>	10	X-ray & longitudinal resonance
	<b>Viscan Plus</b>	20	Longitudinal resonance & X-ray density
	<b>Viscan Compact</b>	22	Longitudinal resonance & density
	<b>Viscan portable with balance</b>	29	Portable, longitudinal resonance & density
	<b>Viscan portable without balance</b>	30	Portable, longitudinal resonance
Microtec AB (Microtec Linköping)	<i>WoodEye Strength Grader</i>	31	Longitudinal resonance, density & laser tracheid grain angle
Microtec Innovating Wood Oy (Microtec Espoo)	<i>Finscan Nova</i>	36	Camera scanning (visual & near infrared)
	<i>Finscan HD</i>	37	Camera scanning (visual)
Dynalyse AB	<i>Dynagrade</i>	7	Longitudinal resonance
	<b>Precigrader</b>	12	Longitudinal resonance & density
Brookhuis Applied Technologies BV	<b>MTG 960</b>	11	Portable, longitudinal resonance & density
	<b>mtgESCAN 962/966</b>	14	Longitudinal resonance & density
	<b>MTG 920</b>	19	Portable, longitudinal resonance
	<b>MTGbatch 962/966</b>	23	Longitudinal resonance & density
	<b>MTGbatch 922/926</b>	24	Longitudinal resonance
	<b>mtgESCAN 922/926</b>	26	Longitudinal resonance
Dimter GmbH	<i>Grademaster</i>	13	Longitudinal resonance, density & knots
Luxscan technologies	<b>EScan FWM/FW</b>	14	Longitudinal resonance & density
	<b>EScan FM/F</b>	26	Longitudinal resonance
	<i>OptiStrength XE</i>	33	X-ray & longitudinal resonance
	<i>OptiStrength X</i>	34	X-ray
Concept Bois Structure SARL	<i>Triomatic</i>	15	Ultrasonic time of flight & pin indentation density
Automatisation J.R.T Inc	<i>CRP</i>	16	Mechanical bending
XYLOMECA	<i>Xyloclass T</i>	17	Longitudinal resonance & density
	<i>Xyloclass F</i>	21	Flexural resonance & density
SARL Esteves	<i>Noesys</i>	18	Flexural resonance & density
Rosén & Co Maskin	<i>Rosgrade</i>	25	Longitudinal resonance
	<i>Rosgrade plus</i>	28	Longitudinal resonance & density
Innodura	<i>E-CONTROL model AC</i>	27	Longitudinal resonance & density
RemaSawco AB	<i>RS Strength Grader</i>	32	Laser tracheid grain angle
	<i>RS Strength Grader Density</i>	39	Laser tracheid grain angle & density
Ilkon	<i>STIG</i>	35	Portable, longitudinal resonance
M. Manfred Hudel	<i>MODULO</i>	38	Mechanical bending

\*ID relates to the TG1 machine number for naming the ITT reports (settings tables). Note that machines 14 and 26 have different names depending on the manufacturer providing it.

**Table 7.** Machine settings for British spruce WPCS (*Picea sitchensis*, *P. abies*).

Source	Size (mm) & report by	Combinations	[Machine] & table	Reference
UK IE	35-75 × 60-300 UKTGC <i>Timbersolve</i>	[C24/C16] [C18] [C16]	[1]-1	TG2/0801/03 TG1/0211/15
UK IE	35-75 × 60-300 UKTGC <i>Timbersolve</i>	[C24/C16] [C18] [C16]	[2]-1	TG2/0801/03 TG1/0211/15
UK IE	35-80 × 70-260 HFM	[C24/C16] [C16]	[5]-1a also [10]	EN14081-4:2009 TG1/1005/08
UK IE	35-82 × 57-275 Napier <i>Uni</i>	[C24/C16] [C22/C14] [C18] [C16]	[5]-17 also [10]	TG1/0211/13rev
UK IE	20-83 × 47-275 (*A) <i>Napier Uni</i>	[C24/C16] [C22/C14] [C18] [C16] [C16+]	[5]-34 also [10]	TG1/201410/38rev2
UK IE	34-83 × 57-275 Napier <i>Uni</i>	[C24/C16] [C22/C14] [C20/C14] [C18] [C16] [C24/C16+] [C16+]	[5]-48 also [10]	TG1/201703/21rev
UK IE	20-52 × 35-67 (*B) <i>Napier Uni</i>	[C14] [batten14] [batten12] [batten10]	[5]-54 also [10]	TG1/201810/16
UK IE	35-82 × 57-275 Napier <i>Uni</i>	[C22/C14] [C18] [C16]	[8]-18 also [10] [20] [22]	TG1/0211/10rev
UK IE	20-83 × 47-275 (*A) <i>Napier Uni</i>	[C22/C14] [C18] [C16] [C16+]	[8]-32 also [10] [20] [22]	TG1/201410/35
UK IE	34-83 × 57-275 Napier <i>Uni</i>	[C24/C16] [C22/C14] [C20/C14] [C18] [C16] [C24/C16+] [C16+]	[8]-45 also [10] [20] [22]	TG1/201703/25rev
UK IE	35-82 × 57-275 Napier <i>Uni</i>	[C27/C16] [C24/C16] [C22/C14] [C18] [C16] [TR26/C16]	[10]-22	TG1/0211/14rev
UK IE	20-83 × 47-275 (*A) <i>Napier Uni</i>	[C27/C16] [C24/C16] [C22/C14] [C18] [C16] [TR26/C16] [C16+]	[10]-43	TG1/201410/39
UK IE	34-83 × 57-275 Napier <i>Uni</i>	[C27/C16] [C24/C16] [C22/C14] [C20/C14] [C18] [C16] [C27/C16+] [TR26/C16] [TR26/C16+] [C24/C16+] [C16+]	[10]-58	TG1/201703/22rev
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C24/C16] [C22/C14] [C20] [C18] [C16]	[11]-13	TG1/201410/34rev
UK IE	34-84 × 84-168 Napier <i>Uni</i>	[C27/C16] [C24/C16] [C22/C14] [C20] [C18] [C16] [NapierSA/ NapierSC] [NapierSB/NapierSD]	[11]-18	TG1/201703/27rev
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C18] [C16] for grading while green	[11]-22	TG1/201410/40rev2
UK IE	20-52 × 35-54 (*B) <i>Napier Uni</i>	[C14]	[11]-33	TG1/201807/02rev
UK IE	34-82 × 69-247 FCBA	[C27/C18] [C27/C16] [C24/C16] [C24] [C18] [C16] [TR26/C16] [TR26]	[12]-9	TG1/1011/11rev
UK IE	34-83 × 57-247 (*C) RISE	[TR26/C16] [C27/C18] [C27/C16] [C24/C16] [TR26] [C24] [C18] [C16]	[12]-20	TG1/202104/11
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C24/C16] [C24/C14] [C22/C14] [C22] [C20] [C18] [C16] [C16+]	[14]-14	TG1/201410/34rev
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C22] [C20] [C18] [C16] for grading while green	[14]-26	TG1/201410/40rev2
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C20] [C18] [C16]	[19]-10	TG1/201410/33rev
UK IE	35-82 × 57-275 Napier <i>Uni</i>	[C24/C16] [C22/C14] [C18] [C16]	[20]-6 also [10]	TG1/0211/12rev
UK IE	20-83 × 47-275 (*A) <i>Napier Uni</i>	[C24/C16] [C22/C14] [C18] [C16] [C16+]	[20]-25 also [10]	TG1/201410/37
UK IE	34-83 × 57-275 Napier <i>Uni</i>	[C27/C16] [C24/C16] [C22/C14] [C20/C14] [C18] [C16] [C27/C16+] [TR26/C16] [TR26/C16+] [C24/C16+] [C16+]	[20]-39 also [10]	TG1/201703/24rev
UK IE	35-82 × 57-275 Napier <i>Uni</i>	[C24/C16] [C22/C14] [C18] [C16]	[22]-4 also [10]	TG1/0211/11rev
UK IE	20-83 × 47-275 (*A) <i>Napier Uni</i>	[C24/C16] [C22/C14] [C18] [C16] [C16+]	[22]-24 also [10]	TG1/201410/36
UK IE	34-83 × 57-275 Napier <i>Uni</i>	[C27/C16] [C24/C16] [C22/C14] [C20/C14] [C18] [C16] [C27/C16+] [TR26/C16] [TR26/C16+] [C24/C16+] [C16+]	[22]-37 also [10]	TG1/201703/23rev
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C24/C16] [C24/C14] [C22/C14] [C22] [C20] [C18] [C16] [C16+]	[23]-13	TG1/201410/34rev
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C22] [C20] [C18] [C16] for grading while green	[23]-25	TG1/201410/40rev2
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C22/C14] [C20] [C18] [C16]	[24]-10	TG1/201410/33rev
UK IE	20-83 × 47-165 (*A) <i>Napier Uni</i>	[C22/C14] [C20] [C18] [C16]	[26]-10	TG1/201410/33rev
UK IE	34-83 × 57-275 Napier <i>Uni</i>	[C24/C16] [C22/C14] [C18] [C16] [TR26/C16] [TR26/C16+] [C24/C16+]	[29]-20 also [10] [22]	TG1/201703/23rev
UK IE	34-83 × 57-275 Napier <i>Uni</i>	[C22/C14] [C18] [C16]	[30]-18 also [8] [10] [20] [22]	TG1/201703/25rev

(\*A): Minimum cross-section area  $\geq 1600 \text{ mm}^2$ .(\*B): Minimum cross-section area  $\geq 900 \text{ mm}^2$ .(\*C): Minimum cross-section area  $\geq 2155 \text{ mm}^2$ .

pass visual grading. This is not incorrect grading, since grading is about the collective properties of the graded timber and not the properties of any

particular piece. Visual grading and different grading machines will achieve the required collective properties of the graded timber by different sorting criteria.

**Table 8.** Machine settings for British pine WPNN (*Pinus sylvestris*, *P. nigra*).

Source	Size (mm) & report by	Combinations	[Machine] & table	Reference
UK IE	35-75 × 60-300 UKTGC	[C24/C16] [C16]	[1]-1	EN14081-4:2009 TG2/0801/02
UK IE	35-75 × 60-300 UKTGC	[C24/C16] [C16]	[2]-1	EN14081-4:2009 TG2/0801/02

Note also that the United Kingdom is officially GB in ISO3166-1, but sometimes appears in standards and settings tables as UK. UK is used in this paper as the

more familiar abbreviation. In the context of growth areas, Northern Ireland is included with this use of the abbreviation GB.

**Table 9.** Machine settings for larch WLAD (*Larix decidua*, *L. x eurolepis*, *L. kaempferi*).

Source	Size (mm) & report by	Combinations	[Machine] & table	Reference
UK	43-82 × 92-250 <i>Timbersolve</i>	[C27/C16] [C18] [C16]	[1]-4	TG2/0801/03 TG1/0511/02
UK	43-82 × 92-250 <i>Timbersolve</i>	[C27/C16] [C18] [C16]	[2]-5	TG2/0801/03 TG1/0511/02
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[5]-31 also [10]	TG1/201410/ 21rev1
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C16] [TR26/C14]	[5]-73 also [10]	TG1/202005/ 07rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[8]-29 also [10] [20] [22]	TG1/201410/18
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C16] [TR26/C14]	[8]-61 also [10] [20] [22]	TG1/202005/ 06rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[10]-39	TG1/201410/22
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C16] [TR26/C14]	[10]-84	TG1/202005/ 08rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [C20] [TR26/C16]	[11]-12	TG1/201410/32
UK	42-112 × 88-307 <i>Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [C20] [NapierLA/NapierLC] [NapierLB/NapierLD]	[11]-19	TG1/201703/ 26rev
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C30/C18] [C27/C16] [C24/C16] [C24/C14] [C22] [C20] [NapierLA/NapierLC] [NapierLB/NapierLD] [TR26/C14]	[11]-29	TG1/202005/ 14rev1
UK	32-110 × 60-248 RISE	[C24/C16] [C18] [C16]	[12]-18	TG1/201810/ 11rev
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[14]-16	TG1/201410/32
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C30/C18] [C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22] [NapierLA/NapierLC] [NapierLB/NapierLD] [TR26/C14]	[14]-35	TG1/202005/ 14rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [C20] [TR26/C16]	[19]-9	TG1/201410/ 31rev
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22] [C20] [NapierLB/NapierLD] [TR26/C16]	[19]-14	TG1/202005/ 14rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[20]-22 also [10]	TG1/201410/ 20rev
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C16] [TR26/C14]	[20]-61 also [10]	TG1/202005/ 05rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[22]-21 also [10]	TG1/201410/19
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C16] [TR26/C14]	[22]-61 also [10]	TG1/202005/ 04rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[23]-15	TG1/201410/32
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C30/C18] [C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22] [NapierLA/NapierLC] [NapierLB/NapierLD] [TR26/C14]	[23]-34	TG1/202005/ 14rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[24]-9	TG1/201410/ 31rev
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22] [NapierLB/NapierLD] [TR26/C16] [TR26/C14]	[24]-14	TG1/202005/ 14rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [TR26/C14]	[26]-9	TG1/201410/ 31rev
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22] [NapierLB/NapierLD] [TR26/C16] [TR26/C14]	[26]-14	TG1/202005/ 14rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C20] [TR26/C16]	[29]-11 also [10] [22]	TG1/201410/23
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C35/C18] [C30/C16] [C27/C16] [C24/C14] [C22] [C20] [TR26/C16] [TR26/C14]	[29]-37 also [10] [22]	TG1/202005/ 04rev1
UK	20-110 × 47-303 (*D) <i>Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C20] [TR26/C16]	[30]-9 also [8] [10] [20] [22]	TG1/201410/23
UK IE	20-110 × 42-303 (*A) <i>NUI Galway &amp; Napier Uni</i>	[C30/C16] [C27/C16] [C24/C14] [C22] [C20] [TR26/C16] [TR26/C14]	[30]-29 also [8] [10] [20] [22]	TG1/202005/ 06rev1

(\*A): Minimum cross-section area  $\geq 1600 \text{ mm}^2$ .

(\*D): Minimum cross-section area  $\geq 2000 \text{ mm}^2$ .

**Table 10.** Machine settings for Douglas-fir PSMN (*Pseudotsuga menziesii*).

Source	Size (mm) & report by	Combinations	[Machine] & table	Reference
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C35/C18] [C35/C16] [C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22/C14] [C20/C14] [C20] [C18] [C16] [TR26/C16]	[5]-53 also [10]	TG1/201804/16
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22/C14] [C20/C14] [C20] [C18] [C16] [TR26/C16]	[8]-47 also [10] [20] [22]	TG1/201804/17rev2
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C40/C30/C16] [C40/C27/C16] [C40/C24/C16] [C35/C18] [C35/C16] [C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22/C14] [C20/C14] [C20] [C18] [C16] [TR26/C16]	[10]-63 & 64	TG1/201804/13rev2
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C35/C16] [C24/C14] [TR26/C14] [NapierDA/NapierDC] [NapierDB/NapierDD]	[11]-24	TG1/201804/25rev
UK BE <sup>1</sup>	32-110 × 60-247 (*E) RISE	[TR26/C16] [C24/C18] [C24] [C18] [C16]	[12]-19	TG1/202005/03rev1
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C35/C16] [C24/C16] [C24/C14] [TR26/C14] [NapierDA/NapierDC] [NapierDB/NapierDD]	[14]-28	TG1/201804/25rev
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C27/C16] [C24/C14] [TR26/C16]	[19]-77	TG1/201804/25rev
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C40/C30/C16] [C40/C27/C16] [C40/C24/C16] [C35/C18] [C35/C16] [C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22/C14] [C20] [C18] [C16] [TR26/C16]	[20]-42 also [10]	TG1/201804/15rev1
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C40/C30/C16] [C40/C27/C16] [C40/C24/C16] [C35/C18] [C35/C16] [C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22/C14] [C20] [C18] [C16] [TR26/C16]	[22]-40 also [10]	TG1/201804/14rev1
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C35/C16] [C24/C16] [C24/C14] [TR26/C14] [NapierDA/NapierDC] [NapierDB/NapierDD]	[23]-27	TG1/201804/25rev
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C27/C16] [C24/C16] [TR26/C16]	[24]-77	TG1/201804/25rev
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C27/C16] [C24/C16] [TR26/C16]	[26]-77	TG1/201804/25rev
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C40/C30/C18] [C40/C27/C16] [C40/C24/C16] [C35/C18] [C35/C16] [C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22/C14] [C20/C14] [C20] [C18] [C16] [C14] [TR26/C16]	[29]-21&22 also [10] [22]	TG1/201804/14rev1
UK IE	33-84 × 68-248 <i>Napier Uni &amp; NUI Galway</i>	[C30/C16] [C27/C16] [C24/C16] [C24/C14] [C22/C14] [C20/C14] [C20] [C18] [C16] [C14] [TR26/C16]	[30]-79 also [8] [10] [20] [22]	TG1/201804/17rev2

<sup>1</sup>BE: Belgium.(\*E): Minimum cross-section area ≥ 2840 mm<sup>2</sup>

## Developments in grading

The timber industry is not oblivious to innovations, and the use of machines for timber quality assessment using acoustic principles is well known in the sector. Since UK and Irish grown timber is mostly grade limited by its stiffness, this technique also has potential for segregation of logs before processing and grading, and also means that strength grading can be carried out by relatively simple longitudinal resonance machines (Table 6) with comparable yields to those from more complicated machines (Gil-Moreno et al. 2019b).

The large-scale multi-partner research work of the Gradewood (Ranta-Maunus 2009 and Ranta-Maunus et al. 2011) and Gradewood Transition projects, the relative simplicity of this acoustic method, and the high repeatability of this kind of measurement, led to the inclusion, in the standard EN14081-2:2018, of fixed settings to grade two of the most important species in Europe: Norway spruce (*Picea abies*) and Silver fir (*Abies alba*) (the combination ‘spruce and fir whitewood’, WPCA), for the grade combinations C24/C18 and T14/T11 as well as for C24, C18, T14 and T1 as single grades. This means any approved grading machines measuring longitudinal resonant frequency can grade these two species within the specified limitations for timber size and additional requirements for operation and environment and without need for further approval by TG1. The settings cover most of the European countries, and therefore will typically result in lower yields than settings

developed for the specific characteristics of a particular timber source. All longitudinal resonance based machines listed in Table 6 are able to use the EN14081-2 fixed settings tables. They do not have to be repeated in the machine’s settings tables, although in some cases they are.

Software development is another important field of innovation, since modern machines are able to do more than sort by simple thresholds. Some manufacturers include, in their machines, functions that allow grading of pieces before splitting into smaller cross sections. More recently, an alternative to the common machine grading by machine control has also been added to EN14081-2; the adaptive settings method. This method uses information previously collected by the machine in the grading process, and aims to automatically adjust the settings, adapting to the variability in the incoming timber, and producing a more optimised balance of yield and safety. This is not implemented in any UK or Irish sawmills where it is unlikely to provide a grading advantage for a relatively uniform resource from a relatively small geographical area. Some sawmills instead optimise their production through log pre-grading, which can reduce rejects from grading and visual override by avoiding the processing of logs likely to give problems. Powerful log pre-grading approaches have the potential to cause issues for structural timber grading if they significantly change the resource compared to what the grading settings and assignments are based on, but research is being done to develop new grading approaches to



adjust for that, e.g. Weidenhiller et al. 2021. Computer tomography (CT) scanning of logs also brings the potential to grade timber before it is sawn from the log in future (e.g. Fredriksson et al. 2017 and Olofsson et al. 2019).

## Concluding remarks

Timber grading in Europe is fast developing, with new machines, updating of standards and processes, and new visual grading assignments and machine grading settings added regularly. There are grading machine settings for timber grown in the UK and Ireland, which exceed the commonly held expectations of what strength classes are possible. Not all the permitted settings have commercially viable yields, but there are some grading possibilities that open up more potential for wider, and more efficient, use of the domestic forest resource, especially as machine grading becomes more accessible to building fabricators.

Contact machine manufacturer or a Notified/Approved Body to obtain more information about grading settings tables, their limitations and yields. As things change, a supplement of this summary may be obtained from <http://blogs.napier.ac.uk/cwst/tg1/>

## ACKNOWLEDGEMENTS

The majority of this work, which includes both wood properties research and standardisation support for the industry, is due thanks to the funders of SIRT (Strategic Integrated Research in Timber) and linked projects in the UK, and the WoodProps programme in Ireland. It is also built upon the work of many people, and particular thanks are due to Stefan Lehneke, John Moore, Steven Adams, Thomas Drewett, James Ramsay, Gregory Searles, Paul McLean, Andrew Lyon, Luka Krajnc, Conan O’Ceallaigh, Colm Walsh, Peter Fahy, and to colleagues at Forest Research, Teagasc and the University of Glasgow. The authors are grateful to grading machine manufacturers Microtec and Brookhuis, and in particular to Martin Bacher of Microtec for all his help over the years.

SIRT, and its allied projects, have received funding or significant in-kind support from the Scottish Higher Education Funding Council, Scottish Forestry, Natural Resources Wales, Forestry Commission England, The Scottish Forestry Trust, Adam Wilson and Sons, Balcas, BSW Timber, James Callander and Son, Confor, Euroforest, Howie Forest Products, James Jones and sons, John Gordon and son, Pontrilas Timber, Scottish Woodlands, UPM Tihill, Glennon Brothers, Murray Timber Group, the Timber Trade Federation, the European Regional Development Fund, Scottish Enterprise and Coillte. Particular thanks are due to Andy Leitch for all his enabling work in recent years, and to John Kissock and Tony Fewell, and other members of the UK Timber Grading Committee for their key role in connecting the researchers to grading in industry.

WoodProps was funded by the Forest Sector Development Division of the Department of Agriculture, Food and the Marine, Ireland, and received significant in-kind support from Coillte, Murray Timber Group and ECC Timber Products. Additional funding was provided by the Higher Education Authority and the Department of Further and Higher Education, Research, Innovation and Science in Ireland.

## Disclosure statement

No potential conflict of interest was reported by the author(s).

## ORCID

Dan Ridley-Ellis  <http://orcid.org/0000-0001-9866-5649>

David Gil-Moreno  <http://orcid.org/0000-0002-5680-1830>

Annette M. Harte  <http://orcid.org/0000-0001-6926-7510>

## References

### Articles:

- Fredriksson M, Broman O, Sandberg D. 2017. The Use of CT-scanning Technology in Wood Value-Chain Research and in Wood Industry: A State of the Art. *Pro Ligno*. 13(4):533–539.
- Gil-Moreno D, O’Ceallaigh C, Ridley-Ellis D, Harte AM. 2019a. Use of Nondestructive Techniques for Determination of Tension Parallel-to-Grain Properties of Spruce. *Proceedings of the 21st International Nondestructive Testing and Evaluation of Wood Symposium*. September 24–27. Freiburg im Breisgau, BW, Germany. PP. 233–240.
- Gil-Moreno D, Ridley-Ellis D, Harte AM. 2019b. Timber grading potential of Douglas fir in the Republic of Ireland and the UK. *International Wood Products Journal*. 10(2):64–69.
- Lycken A, Ziethén R, Olofsson D, Fredriksson M, Brüchert F, Weidenhiller A, Broman O. 2020. State of the art summary on industrial strength grading, including standards, RISE Report 2020:92, ISBN: 978-91-89167-77-3, RISE Research Institutes of Sweden AB, Stockholm.
- McLean P. 2019. Wood properties and uses of Scots pine in Britain, Forestry Commission Research Report FCRP029, Forestry Commission, ISBN: 978-0-85538-985-7.
- Moore J. 2011. Wood properties and uses of Sitka spruce in Britain. Forestry Commission Research Report FCRP015, Forestry Commission, ISBN 978-0-85538-825-6.
- Moore J, Lyon A, Searles G, Lehneke S, Macdonald E. 2008. Scots Pine Timber Quality in North Scotland. Report on the investigation of Mechanical Properties of Structural Timber from three stands. Center for Timber Engineering. Edinburgh, Scotland.
- Moore JR, Lyon AJ, Searles GJ, Lehneke SA, Ridley-Ellis DJ. 2013. Within-and between-stand variation in selected properties of Sitka spruce sawn timber in the UK: implications for segregation and grade recovery. *Ann For Sci*. 70(4):403–415.
- Ó Fátharta C, Gil-Moreno D, Harte AM. 2020. Characterisation of Irish-grown Scots pine timber for structural applications. *Civil Engineering Research in Ireland 2020 (CERI 2020)*.
- Olofsson L, Möller C-J, Wendel C, Oja J, Broman O. 2019. New possibilities with CT scanning in the forest value

- chain. Proceedings 21st International Nondestructive Testing and Evaluation of Wood Symposium, Freiburg, Germany 2019, 569–576.
- Ranta-Maunus A. 2009. Strength of European timber - Part 1. Analysis of growth areas based on existing test results, VTT Publications 706, ISBN 978-951-38-7337-0.
- Ranta-Maunus A, Denzler JK, Stapel P. 2011. Strength of European timber - Part 2. Properties of spruce and pine tested in Gradewood project, VTT Working Papers 179, ISBN 978-951-38-7521-3.
- Ridley-Ellis D. 2020. Grade in Britain: enabling a wider range of home-grown species, Timber 2020 Industry Yearbook, BM TRADA, ISBN: 978-1-909594-83-8, 132-137.
- Ridley-Ellis D, Adams S, Lehneke S. 2016b. Thinking beyond the usual strength grades – with examples of British spruce and larch. Proceedings of the World Conference on Timber Engineering (WCTE 2016), August 22–25, 2016, Vienna, Austria, ISBN 978-3-903039-00-1
- Ridley-Ellis D, Stapel P, Baño V. 2016a. Strength grading of sawn timber in Europe: an explanation for engineers and researchers. Eur J Wood Wood Prod. 74(3):291–306.
- Trussed Rafter Association. 2021. Technical Card: Characteristic Properties of TR26, Trussed Rafter Association. MI. 0006–2021. /08.
- Weidenhiller A, Huber JAJ, Broman O, Fredriksson M, Brüchert F, Sauter UH, Lycken A, Ziethén R, Oja J. 2021. Improved strength grading based on log and board measurements - review and outlook: the research project READiStrength. Proceedings of the World Conference on Timber Engineering (WCTE 2021), August 9-12, 2021, Santiago, Chile
- Standards (note that all the ENs and ISO are also British and Irish Standards):**
- BS4978:2007+A2:2017. Visual strength grading of softwood. Specification. London: British Standards Institution.
- BS5268-2:2002. Structural use of timber. Code of practice for permissible stress design, materials and workmanship. London: British Standards Institution.
- BS5756:2007+A2:2017. Visual strength grading of temperate hardwood. Specification. London: British Standards Institution.
- BSEN1995-1-1:2004+A2:2014. Eurocode 5: design of timber structures. General. Common rules and rules for buildings, including the UK National Annex. London: British Standards Institution.
- EN13556:2003. Round and sawn timber. Nomenclature of timbers used in Europe. Brussels: European Committee for Standardization.
- EN14081-1:2005+A1:2011. Timber structures – strength graded structural timber with rectangular cross section. Part 1: General requirements. Brussels: European Committee for Standardization. withdrawn, superseded, but Harmonized / Designated Standard.
- EN14081-1:2016+A1:2019. Timber structures – strength graded structural timber with rectangular cross section. Part 1: General requirements. Brussels: European Committee for Standardization.
- EN14081-2:2018. Timber structures. Strength graded structural timber with rectangular cross section. Machine grading; additional requirements for type testing. Brussels: European Committee for Standardization.
- EN14081-4:2009. Timber structures. Strength graded structural timber with rectangular cross section. Machine grading. Grading machine settings for machine controlled systems. Brussels: European Committee for Standardization. withdrawn.
- EN1912:2012. Structural timber. Strength classes. Assignment of visual grades and species. Brussels: European Committee for Standardization.
- EN338:2016. Structural timber. Strength classes. Brussels: European Committee for Standardization.
- EN384:2016+A1:2018. Structural timber – determination of characteristic values of mechanical properties and density. Brussels: European Committee for Standardization.
- I.S. 127:2015. Structural timber – visual strength grading – sawn softwoods with rectangular cross-section. National Standards Authority of Ireland.
- ISO3166-1:2020. Codes for the representation of names of countries and their subdivisions. Country codes. Geneva: International Organization for Standardization.
- PD6693-1:2019. Recommendations for the design of timber structures to Eurocode 5: design of timber structures. General. Common rules and rules for buildings. London: British Standards Institution.
- CEN TC124 WG2 TG1 Approved grading reports (confidential):**
- Fewell AR. 2001. TG2/0801/02: Derivation of grading machine settings for UK pine using the method proposed in prEN14081.
- Fewell AR. 2001. TG2/0801/03: Derivation of grading machine settings for UK spruce using the method proposed in prEN14081.
- Gil-Moreno D, Ridley-Ellis D. 2020. TG1/202005/04rev1: Derivation of Viscan Compact and Viscan portable with balance grading machine settings for Larch (IE & GB, C classes).
- Gil-Moreno D, Ridley-Ellis D. 2020. TG1/202005/05rev1: Derivation of Viscan Plus machine settings for Larch (IE & GB, C classes).
- Gil-Moreno D, Ridley-Ellis D. 2020. TG1/202005/06rev1: Derivation of Viscan and Viscan portable without balance grading machine settings for Larch (IE & GB, C classes).
- Gil-Moreno D, Ridley-Ellis D. 2020. TG1/202005/07rev1: Derivation of Goldeneye 702 grading machine settings for Larch (IE & GB, C classes).
- Gil-Moreno D, Ridley-Ellis D. 2020. TG1/202005/08rev1: Derivation of Goldeneye 706 grading machine settings for Larch (IE & GB, C classes).
- Gil-Moreno D, Ridley-Ellis D. 2020. TG1/202005/14rev1: Derivation of MTG grading machine settings for Larch (IE & GB, C classes).
- Glos P, Denzler JK. 2005. TG1/1005/08: Derivation of Grading Machine Settings for Sitka Spruce using the Method proposed in prEN 14081.
- Marcroft J. 2011. TG1/0211/15: Derivation of Grading Machine Settings for British Spruce for Cook Bolinder and Computermatic/Micromatic Grading Machines.
- Marcroft J. 2011. TG1/0511/02: Derivation of Grading Machine Settings for Larch for Cook Bolinder and Computermatic/Micromatic Grading Machines.
- Reuling D, Duccini JC, Perstorper M. 2011. TG1/1011/11rev: Sitka spruce and Norway spruce from United Kingdom and Ireland for the Grading Machine Precigrader based on EN14081-2.
- Ridley-Ellis D. 2014, revised 2018. TG1/201410/20rev: Derivation of ViSCAN-PLUS grading machine settings for UK larch.
- Ridley-Ellis D. 2014, revised 2018. TG1/201410/38rev2: Derivation of GoldenEye-702 grading machine settings for British spruce.

- Ridley-Ellis D. 2014, revised 2018. TG1/201410/40rev2: Derivation of MTG 960, mtgBATCH 962 and mtgBATCH 966 grading machine settings for green British spruce.
- Ridley-Ellis D. 2014. TG1/201410/18: Derivation of ViSCAN grading machine settings for UK larch.
- Ridley-Ellis D. 2014. TG1/201410/19: Derivation of ViSCAN-COMPACT grading machine settings for UK larch.
- Ridley-Ellis D. 2014. TG1/201410/21rev1: Derivation of GoldenEye-702 grading machine settings for UK larch.
- Ridley-Ellis D. 2014. TG1/201410/22: Derivation of GoldenEye-706 grading machine settings for UK larch.
- Ridley-Ellis D. 2014. TG1/201410/23: Derivation of ViSCAN-portable grading machine settings for UK larch.
- Ridley-Ellis D. 2014. TG1/201410/31rev: Derivation of MTG 920, mtgBATCH 922 and mtgBATCH 926 grading machine settings for UK larch.
- Ridley-Ellis D. 2014. TG1/201410/32: Derivation of MTG 960, mtgBATCH 962 and mtgBATCH 966 grading machine settings for UK larch.
- Ridley-Ellis D. 2014. TG1/201410/33rev: Derivation of MTG 920, mtgBATCH 922 and mtgBATCH 926 grading machine settings for British spruce.
- Ridley-Ellis D. 2014. TG1/201410/34rev: Derivation of MTG 960, mtgBATCH 962 and mtgBATCH 966 grading machine settings for British spruce.
- Ridley-Ellis D. 2014. TG1/201410/35: Derivation of ViSCAN grading machine settings for British spruce.
- Ridley-Ellis D. 2014. TG1/201410/36: Derivation of ViSCAN-COMPACT grading machine settings for British spruce.
- Ridley-Ellis D. 2014. TG1/201410/37: Derivation of ViSCAN-PLUS grading machine settings for British spruce.
- Ridley-Ellis D. 2014. TG1/201410/39: Derivation of GoldenEye-706 grading machine settings for British spruce.
- Ridley-Ellis D. 2017. TG1/201703/21rev Derivation of Goldeneye 702 grading machine settings for British spruce.
- Ridley-Ellis D. 2017. TG1/201703/22rev Derivation of Goldeneye 706 grading machine settings for British spruce.
- Ridley-Ellis D. 2017. TG1/201703/23rev Derivation of Viscan Compact and Viscan portable with balance grading machine settings for British spruce.
- Ridley-Ellis D. 2017. TG1/201703/24rev Derivation of Viscan Plus grading machine settings for British spruce.
- Ridley-Ellis D. 2017. TG1/201703/25rev Derivation of Viscan and Viscan portable without balance grading machine settings for British spruce.
- Ridley-Ellis D. 2017. TG1/201703/26rev Derivation of MTG 960 grading machine settings for UK larch.
- Ridley-Ellis D. 2017. TG1/201703/27rev Derivation of MTG 960 grading machine settings for British spruce.
- Ridley-Ellis D. 2018. TG1/201807/02rev: Derivation of MTG 960 grading machine settings for British spruce tiling battens.
- Ridley-Ellis D. 2018. TG1/201810/16: Derivation of Goldeneye 702 grading machine settings for British spruce tiling battens.
- Ridley-Ellis D, Gil-Moreno D. 2018. TG1/201804/13rev2: Derivation of Goldeneye 706 grading machine settings for Douglas fir (IE & GB, C classes).
- Ridley-Ellis D, Gil-Moreno D. 2018. TG1/201804/14rev1: Derivation of Viscan Compact and Viscan portable with balance grading machine settings for Douglas fir (IE & GB, C classes).
- Ridley-Ellis D, Gil-Moreno D. 2018. TG1/201804/15rev1: Derivation of Viscan Plus machine settings for Douglas fir (IE & GB, C classes).
- Ridley-Ellis D, Gil-Moreno D. 2018. TG1/201804/16: Derivation of Goldeneye 702 grading machine settings for Douglas fir (IE & GB, C classes).
- Ridley-Ellis D, Gil-Moreno D. 2018. TG1/201804/17rev2: Derivation of Viscan and Viscan portable without balance grading machine settings for Douglas fir (IE & GB, C classes).
- Ridley-Ellis D, Gil-Moreno D. 2018. TG1/201804/25rev: Derivation of MTG grading machine settings for Douglas fir (IE & GB, C classes).
- Ridley-Ellis D, Moore JR. 2011. TG1/0211/10rev: Derivation of ViSCAN Grading Machine Settings for British spruce.
- Ridley-Ellis D, Moore JR. 2011. TG1/0211/11rev: Derivation of ViSCAN-COMPACT Grading Machine Settings for British spruce.
- Ridley-Ellis D, Moore JR. 2011. TG1/0211/12rev: Derivation of ViSCAN-PLUS Grading Machine Settings for British spruce.
- Ridley-Ellis D, Moore JR. 2011. TG1/0211/13rev: Derivation of GoldenEye-702 Grading Machine Settings for British spruce.
- Ridley-Ellis D, Moore JR. 2011. TG1/0211/14rev: Derivation of GoldenEye-706 Grading Machine Settings for British spruce.
- Ziethén D. 2021. TG1/202104/11: Determination of settings for C-grades according to EN 338 for Precigrader, derived according to EN 14081-2 for British spruce (WPCS) from Ireland and UK.
- Ziethén R. 2018. TG1/201810/11Rev: Determination of settings for C-grades according to EN 338 for Precigrader, derived according to EN 14081-2 for Larch from UK.
- Ziethén R. 2020. TG1/202005/03Rev1: Determination of settings for C-grades according to EN 338 for Precigrader, derived according to EN 14081-2 for Douglas Fir from Belgium and UK.